Evaluation and improvement of IEC 60891 correction methods for I-V curves of defective photovoltaic panels

Baojie Li, Anne Migan-Dubois, Claude Delpha, Demba Diallo

► To cite this version:

Baojie Li, Anne Migan-Dubois, Claude Delpha, Demba Diallo. Evaluation and improvement of IEC 60891 correction methods for I-V curves of defective photovoltaic panels. *Solar Energy*, 2021, 216, pp.225-237. 10.1016/j.solener.2021.01.010 . hal-03237596

HAL Id: hal-03237596

<https://hal-centralesupelec.archives-ouvertes.fr/hal-03237596>

Submitted on 4 Nov 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Evaluation and Improvement of IEC 60891 Correction Methods for I-V Curves of Defective Photovoltaic Panels

Baojie LI^{1,2}, Anne MIGAN-DUBOIS¹, Claude DELPHA², Demba DIALLO^{1*},

¹ Université Paris-Saclay, CentraleSupélec, CNRS, GeePs, Sorbonne Université, 3-11 Rue Joliot Curie, Gif Sur Yvette, 91192, France

² Université Paris-Saclay, CNRS, CentraleSupélec, L2S, 3 Rue Joliot Curie, Gif Sur Yvette, 91192, France

* Corresponding author: demba.diallo@centralesupelec.fr

Abstract: Correction of the I-V curve permits the comparison of curves measured under different conditions for photovoltaic (PV) panels' health monitoring purpose. IEC 60891 has defined three standard procedures named 1, 2 and 3 for the correction. They were initially designed to correct the curves of healthy PV panels. However, their performance, when applied to I-V curves measured on faulty panels, is rarely discussed. This work evaluates these correction methods on I-V curves simulated under different environmental conditions and for five types of defects of varying severity. The results show that procedure 3 has a relatively better overall performance but is not suitable for rapid application in the field as it requires the determination of reference curves. It is found that procedures 1 and 2 could introduce distortion of the curve's shape, with a relative error of up to 13.8 % and 6.4 %, respectively. A misestimation of 9.1 % for key parameters of the curve has been observed, when using procedure 2 for maximum power. Based on the performance analysis, a new correction method is proposed to fit the corrected voltage. It can reduce the curve's average correction error by 31.3 % compared to the original single curve correction method. Challenges and directions for future work are also presented.

Key words: Photovoltaic; I-V curve; I-V curve correction; IEC 60891; Fault detection and diagnosis;

Nomenclature			
a	Irradiance correction factor	V_{oc}^{real}	V_{OC} of real curve at STC (V)
α	Absolute temperature coefficient of I_{SC} (A/°C)	V_{rp}	Voltage of inflexion point under PS (V)
α_{rel}	Relative temperature coefficient of I_{SC} (%/°C)	PS	Partial shading
β	Absolute temperature coefficient of V_{OC} (V/°C)	P_m	Maximum Power (W)
β_{rel}	Relative temperature coefficient of V_{OC} (%/°C)	PV	Photovoltaic
CE	Curve error (%)	OC	Open circuit
G	Global in-plane irradiance (W/m ²)	RE	Relative error (%)
GainPS	Block gain used in simulation to control PS degree	R_{OC}	Resistance used in simulation for OC (Ω)
I	Current (A)	R_s	Series resistance (Ω)
I^c	Current of corrected curve (A)	R_{s_degra}	Resistance used in simulation for R_s degradation (Ω)
I^{real}	Current of real curve at STC (A)	R_{SC}	Resistance used in simulation for SC (Ω)
I_{MPP}	Current at MPP (A)	R_{sh}	Shunt resistance (Ω)
I_{rp}	Current of inflexion point under PS (A)	R_{sh_degra}	Resistance used in simulation for R_{sh} degradation (Ω)
I_{SC}	Short-circuit current (A)	SC	Short circuit
I_{SC}^{real}	I_{SC} of real curve at STC (A)	STC	Standard test condition
I-V curve	Current-voltage characteristics	TC	Temperature coefficient
MPP	Maximum power point	T_m	Module temperature (°C)
κ	Curve correction factor	γ	Interpolation constant for correction method M3
V	Voltage (V)		
V_{MPP}	Voltage at MPP (V)		
V_{OC}	Open-circuit voltage (V)		
V_{OC}^{STC}	V_{OC} under STC in healthy condition (provided in datasheet) (V)		

1. Introduction

The current-voltage characteristics (I-V curves) measured from a faulty photovoltaic (PV) module or array (from now on, termed as faulty I-V curve) contain valuable information on the health status (Fadhel et al., 2019; Li et al., 2019). For a single module or small-scale PV string, one I-V tracer device can measure I-V curves under various meteorological conditions (Sarikh et al., 2020; Zhu and Xiao, 2020). Hardware solutions (integrated at inverter level) (Spataru et al., 2015) support are now commercially available to measure I-V curves at array or power plant level (Huawei, 2020). Therefore, with the increasing availability of field-measured I-V curves, I-V curves for PV health monitoring are becoming a hot topic (Mellit et al., 2018; Pillai and Rajasekar, 2018).

Based on a field-measured I-V curve under any environmental conditions, there are two common ways (Mellit et al., 2018; Pillai and Rajasekar, 2018) to use it for PV health monitoring and diagnosis:

- *Model-based difference analysis*: Analyze the residue between the measured I-V curve (or the extracted features) and the simulated ones for identical environmental condition,
- *Correction-based analysis*: Correct the whole measured I-V curve (or the extracted features) to specific environmental condition (generally Standard Test Condition (STC) (1000 W/m² and 25 °C)).

It is clear that for a model-based difference analysis, it is unnecessary to correct the I-V curve, but a suitable and accurate PV model is required.

However, for correction-based analysis, correction of the I-V curve is an indispensable step to make curves measured under different environmental conditions comparable. Based on the corrected curves, the open-circuit voltage (V_{OC}), short-circuit current (I_{SC}), the voltage at the point of maximum power (V_{MPP}), current (I_{MPP}) and power (P_m) are commonly extracted characteristics for fault diagnosis (Agrawal et al., 2020; Chen et al., 2017; Huang et al., 2019) or power loss analysis (Wang et al., 2020). Besides, equivalent series resistance (R_s) or shunt resistance (R_{sh}) are also commonly calculated from corrected curves to analyze the degradation mode of PV networks (Bouaichi et al., 2019; Silva et al., 2019).

In this sense, if there are significant errors in the corrected curves or the corresponding characteristics, the subsequent PV diagnosis's accuracy will be severely compromised. Therefore, correction of I-V curves plays a vital role in PV health monitoring.

There are no specific methods proposed for the correction of faulty I-V curves to the best of our knowledge. Consequently, most researchers adopt the original or simplified IEC 60891 (IEC 60891, 2009) correction procedures (Golive et al., 2019; Rajput et al., 2016). For example, several authors have adopted the procedure 1 in IEC 60891 to correct I-V curves measured under partial shading (PS) (Dolara et al., 2013), potential induced degradation (PID) (Martínez-Moreno et al., 2018), dust soiling (Tanesab et al., 2017, 2015), or hot spot (Ma et al., 2019). Besides, procedure 2 of IEC 60891 is also used to correct the I-V curves' key parameters (Chen et al., 2017). These parameters can then be used as inputs of a classifier (e.g., artificial neural network (ANN)) to automatically identify the fault types (PS, open circuit (OC), short circuit (SC), or shunt resistance degradation). Similar applications can also be found in (Zhu et al., 2018).

It should be noted that these methods based on the IEC 60891 standard have been all initially designed for the correction of curves measured from healthy PV panels. Moreover, in literature, the suitability of these methods' correction of the I-V curves of defective panels is rarely studied, let alone whether the defects' characteristics are distorted by the correction and thus lead to a diagnostic error. All these issues are decisive for the diagnosis of PV faults (Triki-Lahiani et al., 2018). Thus, this paper aims to first evaluate the IEC 60891 methods' performance for the correction of faulty panels' I-V curves. Then, based on IEC 60891 methods' performance analysis, an improved correction method will be proposed and evaluated.

The outline of the paper is as follows. Section 2 introduces the methodology from the simulation of faulty I-V curves, introduces the correction methods and performance evaluation metrics. Sections 3 and 4 present the correction performance using the single or multiple-curves-based methods, respectively. The comparison of these methods and guidance on future work are discussed in Section 5. Section 6 concludes the paper.

2. Methodology for the evaluation of correction methods

Since our target is to evaluate the error caused by the correction methods, it is essential to avoid the effects of other factors, like the measurement uncertainty on irradiance G , module temperature T_m and I-V curve, which could be up to 5 % (Friesen et al., 2018). Therefore, the curves to be corrected are generated in simulation rather than from field measurement to ensure all the correction formula parameters are real values, without any bias.

2.1. Simulation of I-V curves

2.1.1. Simulation model

A PV array is modelled under Simulink® to address several fault types. The array consists of two strings in parallel, and each string of three mc-Si modules in series, as shown in Fig.1 (a). Each module comprises three strings of twenty cells and three bypass diodes, as shown in Fig.1 (b). Table 1 lists the detailed module parameters.

Condition	GainPS	R_{SC} (Ω)	R_{OC} (Ω)	R_{s_degra} (Ω)	R_{sh_degra} (Ω)
Healthy	1	10^5	10^{-5}	10^{-5}	10^5
PS 1 module	[0-1]	10^5	10^{-5}	10^{-5}	10^5
SC 1 module	1	10^{-5}	10^{-5}	10^{-5}	10^5
OC 1 string	1	10^5	10^5	10^{-5}	10^5
Rs degradation	1	10^5	10^{-5}	$[10^{-5}-2]$	10^5
Rsh degradation	1	10^5	10^{-5}	10^{-5}	$[10^5-10]$

2.2. Correction methods

Through the literature review, the most common I-V curve correction methods are based on three procedures (hereafter, called M1, M2, and M3) proposed in IEC 60891 (IEC 60891, 2009). These methods and a proposed M2-based improved method are detailed as follows:

- Method 1 (M1):

$$I_2 = I_1 + I_{SC1}(G_2/G_1 - 1) + \alpha(T_{m2} - T_{m1}) \quad (1)$$

$$V_2 = V_1 - R_s(I_2 - I_1) - \kappa I_2(T_{m2} - T_{m1}) + \beta(T_{m2} - T_{m1}), \quad (2)$$

where, I_1 and I_2 , V_1 and V_2 , T_{m1} and T_{m2} , G_1 and G_2 are the current, voltage, module temperature, and irradiance before, and after correction, respectively; I_{SC1} is the short-circuit current before correction; α and β are the PV module absolute TC of I_{SC} and V_{OC} , respectively; $\alpha = \alpha_{rel} \cdot I_{SC}^{STC}$, $\beta = \beta_{rel} \cdot V_{OC}^{STC}$, α_{rel} and β_{rel} are the relative TC of I_{SC} and V_{OC} (presented in Table 1); R_s is the internal series resistance and κ is the curve correction factor.

- Method 2 (M2):

$$I_2 = I_1(1 + \alpha_{rel}(T_{m2} - T_{m1}))G_2/G_1 \quad (3)$$

$$V_2 = V_1 + V_{OC1}[\beta_{rel}(T_{m2} - T_{m1}) + a \cdot \ln(G_2/G_1)] - R_s(I_2 - I_1) - \kappa \cdot I_2(T_{m2} - T_{m1}), \quad (4)$$

where, V_{OC1} is the V_{OC} before correction; a is the irradiance correction factor; R_s and κ are determined by the procedure described in (IEC 60891, 2009).

The determination of the coefficients a , R_s and κ for M1 and M2 requires a group of I-V curves at the same G or at the same T_m , which is troublesome and time-consuming to fulfill in real life. Therefore, in most M1 and M2 applications, these coefficients are either tuned via simulation under healthy condition (Silva et al., 2019) or neglected (Dolara et al., 2013) but to the detriment of lower performance. Therefore, in this paper, these coefficients will not be neglected and determined following the standard routine, i.e., via the simulation under healthy condition.

- New Method 2 (NewM2):

In fact, as it will be shown later, M1 and M2 do not perform well under all the tested faulty conditions. Thus, a new method denoted NewM2 is proposed. It uses the same formula as M2 for current correction. But for the voltage correction, the term ' V_{OC1} ' in (4) is replaced by ' $V_{OC1}[1 + \beta_{rel}(25 - T_1)]$ '. The reason for this change will be explained in Section 3.2.1 while analyzing the correction performance. Therefore, the equations for NewM2 are:

$$I_2 = I_1(1 + \alpha_{rel}(T_{m2} - T_{m1}))G_2/G_1 \quad (5)$$

$$V_2 = V_1 + V_{OC1}[1 + \beta_{rel}(25 - T_1)][\beta_{rel}(T_{m2} - T_{m1}) + a \cdot \ln(G_2/G_1)] - R_s(I_2 - I_1) - \kappa \cdot I_2(T_{m2} - T_{m1}) \quad (6)$$

- Method 3 (M3):

Different from M1, M2 or the NewM2, M3 is free from correction coefficient but needs an interpolation constant γ :

$$I_3 = I_1 + \gamma(I_2 - I_1) \quad (7)$$

$$V_3 = V_1 + \gamma(V_2 - V_1) \quad (8)$$

According to (IEC 60891, 2009), M3 requires at least 2 reference curves to obtain one corrected curve at specified G or T_m by calculating γ using (7) or (8). Thus, to correct a curve with a requirement on both G and T_m , three curves are necessary.

$$G_3 = G_1 + \gamma(G_2 - G_1) \quad (9)$$

$$T_3 = T_1 + \gamma(T_2 - T_1) \quad (10)$$

In summary, the implementation of M1, M2, and NewM2 only requires one single I-V curve, while M3 requires multiple curves. Since their correction procedures are different, their evaluation performance will be conducted separately (in Sections 3 and Section 4, respectively). Since STC ($G = 1000 \text{ W/m}^2$ and $T_m = 25 \text{ }^\circ\text{C}$) is more commonly adopted as the target condition for I-V curve-based diagnosis, in the following, if not stated, the correction of I-V curves refers to the correction to STC.

2.3. Performance evaluation metrics

The evaluation of correction performance will be conducted from two aspects, i.e., from the whole I-V curve and single extracted parameters (e.g., maximum power P_m , V_{OC} and I_{SC}). Firstly, for the whole I-V curve, the curve error (CE) is adopted as the metric, calculated by the normalized root-mean-square error between the corrected curve and the one

simulated-at-STC (from now on called real curve). It should be noted that the real curve only means that G and T_m are at STC, but the array condition could be either healthy or faulty.

$$CE = \frac{\sqrt{\frac{1}{N} \sum_{i=1}^N (I_i^c - I_i^{real})^2}}{I_{SC}^{real}} \times 100 \% \quad (11)$$

where, I_i^c and I_i^{real} are the current values from the corrected and actual curve, respectively, for the same voltage V_i . V_i is the i^{th} element of the voltage vector consisting of N points linearly distributed in the interval between 0 and V_{max} with a constant step (V_{max} is constant for all the conditions). The value of V_{max} can be set higher than V_{oc} in order to prevent the voltage after correction from exceeding the set value. In this study, V_{max} is set as 120V and N at 100. I_{SC}^{real} refers to the I_{SC} extracted from the real curve.

Then, regarding the parameters, the correction is evaluated with the relative error (RE):

$$RE_X = \frac{X^c - X^{real}}{X^{real}} \times 100 \% \quad (12)$$

where, X^c and X^{real} are the parameters from the corrected and real curve, respectively. X can be a data coming directly from the curve (such as P_m , V_{OC} or I_{SC}) or one of the parameters of the single-diode model (R_s or R_{sh} for example) whose evolution can be considered as a signature of a defect.

3. Performance of correction methods using single I-V curve

This section focuses on the correction methods based on a single I-V curve, i.e., M1, M2 and NewM2. Firstly, the selection of G and T_m to generate the curves is presented in Section 3.1. Then, the correction performance (using the metrics CE , and RE) will be evaluated using the curves simulated under constant or variable fault severity, presented in sections 3.2 and 3.3, respectively.

3.1. Selection of G and T_m based on field measurement

To evaluate the correction methods with real environmental conditions, the selection of G and T_m to generate the curves is based on field measurement (in SIRTa meteorological and climate observatory (Migan et al., 2015), France) of one mc-Si PV module (identical to those used in the simulation in Section 2.1.1) during summer as illustrated in Fig. 2. To minimize the correction error, commonly, the curves' irradiance for correction is selected in the highest range (Ding et al., 2014). Therefore, in our case studies, the lower bound of G is set as 800 W/m².

Fig. 2 Selected G and T_m based on field-measurement during summer for one mc-Si PV module

In Fig. 2, the blue points represent the measured G and T_m , while the red ones are selected for the simulation. A group of 174 pairs of G and T_m is selected based on a quasi-uniform distribution within the area enclosed by the blue points.

3.2. Correction performance using curves for defects of constant severity

The fault severity is firstly set constant to investigate the impact of the selected G and T_m :

- 1) GainPS = 0.2 for partial shading,

- 2) $R_{s_degra} = 1 \Omega$ for series resistance degradation,
- 3) $R_{sh_degra} = 30 \Omega$ for shunt resistance degradation

Based on the generated curves, the correction performance can now be evaluated. Section 3.2.1 examines the shape of the corrected curves. Section 3.2.2 analyzes the performance evaluation metrics CE and RE for key curve parameters, and Section 3.2.3 studies the RE for the fault features.

3.2.1. Corrected I-V curve form

Using M1, M2 and NewM2, the curves before and after correction are displayed in Fig. 3.

Fig. 3 Correction results, (a): curves simulated for correction (each condition contains 174 curves with field-measured combinations of G and T_m at constant fault severity), (b): corrected curves using M1, (c): corrected curves using M2, (d): corrected curves using NewM2 (the displayed color of each curve is determined by the irradiance value with the colorbar on the right side of the figure, the circles on the curves represent the MPP)

For the corrected curves, apparent deviations to the real I-V curve can be observed for most faulty conditions using the three methods. These deviations are due to the combined effect of voltage and current corrections, reflected along the x and y axes, respectively. They are now analyzed as follows:

1) Voltage correction:

The deviations due to voltage corrections are observable in all the cases when using M2, but only for SC and R_s degradation when using M1, and for SC when using the NewM2. To analyze these results, we rearrange the voltage correction formulas (2), (4), and (6) as it follows:

$$V_2 = k_1 \cdot V_1 + k_2 \cdot (T_{m2} - T_{m1}) + k_3 \cdot \ln(G_2/G_1) + k_4 \cdot (I_2 - I_1) + k_5 \cdot I_2 \cdot (T_{m2} - T_{m1}), \quad (13)$$

where the different coefficients k_i ($i = 1, \dots, 5$) for each method, are given in Table 3.

Table 3 Coefficients for voltage correction in M1, M2 and NewM2

Method	k_1	k_2	k_3	k_4	k_5
M1	1	$\beta_{rel} \cdot V_{OC}^{STC}$	0	$-R_s$	$-k$
M2	1	$\beta_{rel} \cdot V_{OC1}$	$a \cdot V_{OC1}$	$-R_s$	$-k$
NewM2	1	$\beta_{rel} \cdot V_{OC1} \cdot [1 + \beta_{rel}(T_{m2} - T_{m1})]$	$a \cdot V_{OC1}$	$-R_s$	$-k$

* In this study, we correct the curves to STC, thus $T_{m2} = 25^\circ \text{C}$

Firstly, we compare M1 and M2. Based on the tuning procedure in the standard IEC 60891, k_4 and k_5 are similar for the two methods. As for k_3 , it is 0 in M1. In M2, since both the coefficient a and $\ln(G_2/G_1)$ are small values, their product is a second-order term, and its contribution is negligible (within $\pm 0.3\%$). As a consequence, the main difference between M1 and M2 lies in k_2 . It is noteworthy that k_2 for M1 is constant, while for M2, it depends on V_{OC1} (V_{OC} of the curve to correct). In Fig. 3 (b), there is almost no distortion of the corrected curves when using M1 under healthy condition, which demonstrates the voltage's correction efficiency. As for M2, since T_m of the curves to correct (T_{m1}) are all higher than

the target T_m (T_{m2} , 25°C), V_{oc1} is thus always lower than V_{oc}^{STC} (impact of G on V_{oc1} is negligible compared to T_m). Accordingly, $k_2 \cdot (T_{m2} - T_{m1})$ in M2 is lower than in M1. Therefore, the corrected voltage in M2 is lower than in M1. That is the reason why in Fig. 3 (c), we can observe the slight distortions of the corrected curves shifted on the left side of the real curve round the open-circuit point.

Besides, the significant correction error under SC and PS for M1 and M2 also originates from the setting of k_2 . For SC, to be specific, short-circuit is introduced in one module of one string. As a consequence, V_{oc}^{real} is different from V_{oc}^{STC} (value extracted from the datasheet, i.e., in healthy case), and is equal to around 2/3 of V_{oc}^{STC} . Therefore, in M1, the corrected voltage is higher than the real value. As for M2, V_{oc1} , although varying with T_m , is still closer to V_{oc}^{real} . Consequently, voltage correction is more efficient with M2. Regarding PS (1 module shaded), during the process of I-V scan, when the bypass diodes get activated, the shaded module can be considered as a SC. That explains why a similar deviation is also observed near the inflexion point.

From the above analysis, M1 and M2 have their pros and cons in voltage correction. Accordingly, NewM2 is designed by combining their advantages. As observed before, in k_2 , using V_{oc}^{STC} (like in M1) could generally lead to better voltage correction than using V_{oc1} (like in M2) except under SC. The exception is because V_{oc}^{STC} fails to reflect V_{oc}^{real} . Therefore, in NewM2, V_{oc1} is replaced by $V_{oc1} \cdot [1 + \beta_{rel}(T_{m2} - T_{m1})]$, which corrects the measured V_{oc1} to the V_{oc} under STC of the real curve and therefore, could better approximate V_{oc}^{real} under any condition. In this way, as shown in Fig. 3 (d), the correction errors near the open-circuit point using M1 (under SC) and using M2 (under other cases) are attenuated.

2) Current correction:

For the current of corrected curves, noticeable dispersion along the y-axis is observed under PS near the inflexion point using M1. In fact, the output current of the PV module is mainly affected by G , while the impact of T_m is limited. Therefore, to analyze this phenomenon, for simplification, the contribution of ' $(T_{m2} - T_{m1})$ ' is neglected. Then we can derive from (1) and (3):

- For M1:

$$I_2 = I_1 + I_{SC1}(G_2/G_1 - 1) \quad (14)$$

- For M2:

$$I_2 = I_1 \cdot G_2/G_1 \quad (15)$$

Comparing these two expressions, for M2, the corrected current (I_2) is proportional to the current to correct (I_1). While for M1, there is always a bias that degrades correction's performance, particularly around the inflexion point, like in Fig. 3 (b) under PS. Therefore, M2 performs relatively better than M1 in current correction. That also explains why, for NewM2, the current formula of M2 is chosen, and the same performance is achieved in Fig. 3 (d).

3.2.2. CE and RE of key curve parameters

Based on the corrected curves, the performance evaluation metrics (CE , RE_{P_m} , $RE_{V_{oc}}$ and $RE_{I_{SC}}$) are calculated. Considering that G and T_m are both varying for the 174 curves to correct, the statistics of the metrics are presented in Fig. 4.

Fig. 4 Four metrics to present the correction performance of M1, M2 and NewM2: (a) CE , (b) RE of P_m , (c) RE of V_{oc} , (d) RE of I_{sc} (the bars represent the mean value for the correction of 174 curves, while the horizontal whiskers represent the standard deviation (std), these 2 values are marked as 'mean'±'std')

These metrics are analyzed as follows:

- 1) CE : The value of CE , which reflects the correction error on the whole curve, corresponds to the observations in Fig. 3. As expected, high CE is found under SC using M1, and PS using all the methods. None of M1 and M2 outperforms in all the conditions, but the proposed NewM2 performs better with generally lower and more stable CE . The overall average CE (2.37 %) decreased by 31.3 % compared to the average when using M2 (3.45 %);
- 2) RE_{P_m} : Similarly, NewM2 performs better correction of P_m . However, it should be noticed that RE_{P_m} is positive under nearly all the conditions for all the methods. This indicates that the fault impact on P_m is underestimated. The mean maximum value is up to 9.1 %, which could hinder the detection of incipient PV fault if P_m is used as a fault indicator;
- 3) $RE_{V_{OC}}$: The results are consistent with our previous observations, i.e., the corrected V_{OC} with M2 is always lower than the real value under all conditions, while the V_{OC} using M1 is relatively better corrected except under SC, where the maximum value of the mean $RE_{V_{OC}}$ could reach 5.7 %. And NewM2 effectively reduces $RE_{V_{OC}}$ compared with M1 (in SC), and M2 (in other cases);
- 4) $RE_{I_{SC}}$: The performance of the three methods is similar. It should be noted that, based on (2) and (4), the voltage of the short-circuit point on the original curve (i.e., equals 0), after correction, is positive. This phenomenon is also observed in (Bühler et al., 2014). Therefore, to retrieve the I_{SC} (according to the definition, the corresponding voltage should be 0), the corrected curve must be extrapolated. Here, the extrapolation method in (Bühler et al., 2014) is adopted. In this way, although the current value corrected from the original I_{SC} (I_{SC1}) is close to the actual I_{SC} , there is still a difference that depends on the initial slope of the corrected curve. Indeed for all the conditions except Rsh degradation, where the slope is mild, $RE_{I_{SC}}$ is low (within ± 0.5 %). But for Rsh degradation, where the current at MPP is severely lowered down, the slope is steep, and $RE_{I_{SC}}$ is larger.

3.2.3. RE of fault features

Now, we evaluate the correction performance from one or two typical curve parameters, selected as follows:

- 1) PS: The voltage and current at the inflexion point, named V_{rp} and I_{rp} respectively. I_{rp} could reflect the shading level, and V_{rp} the number of activated bypass diodes of PV modules in one string;
- 2) SC: The open-circuit voltage V_{OC} ;
- 3) OC: The short-circuit current I_{SC} ;
- 4) Rs degradation: The extracted R_s from I-V curve, $R_s = -\frac{1}{\frac{dI}{dV}|_{V=V_{OC}}}$ (Chin et al., 2015);
- 5) Rsh degradation: The extracted R_{sh} from I-V curve, $R_{sh} = -\frac{1}{\frac{dI}{dV}|_{I=I_{SC}}}$ (Chin et al., 2015);

For each fault feature, the RE is calculated from the values obtained from the corrected and real curves. The results are summarized in Table 4. We can observe large misestimation (absolute mean $RE > 2$ %) with V_{rp} , I_{rp} , V_{OC} and R_s when using M1, and V_{rp} , R_s and R_{sh} when using M2 and NewM2. Worse yet, nearly all these large errors (except R_{sh} using M2 and NewM2) lead to underestimating fault features, which will affect the detection of incipient faults. Similarly, none of the three methods outperforms for all the fault features. However, the overall performance of NewM2 is relatively better.

Table 4 Impact of correction on fault features using M1, M2 and NewM2

Case	Fault feature	M1		M2		NewM2	
		Value (%) (mean $\pm$ std)	Impact on fault feature	Value (%) (mean $\pm$ std)	Impact on fault feature	Value (%) (mean $\pm$ std)	Impact on fault feature
PS	$RE_{V_{rp}}$	7.3 $\pm$ 2.6	Underestimated	6.8 $\pm$ 1.3	Underestimated	7.4 $\pm$ 1.8	Underestimated
	$RE_{I_{rp}}$	2.5 $\pm$ 6.6	Underestimated	-0.2 $\pm$ 0.1	Overestimated	-0.2 $\pm$ 0.1	Overestimated
SC	$RE_{V_{OC}}$	5.7 $\pm$ 1.4	Underestimated	-0.7 $\pm$ 0.7	Overestimated	1.1 $\pm$ 0.8	Underestimated
OC	$RE_{I_{SC}}$	-0.4 $\pm$ 0.08	Overestimated	0.3 $\pm$ 0.06	Underestimated	0.3 $\pm$ 0.07	Underestimated
Rs degra	RE_{R_s}	-3.4 $\pm$ 0.7	Underestimated	-13.6 $\pm$ 5.1	Underestimated	-5.5 $\pm$ 5.3	Underestimated
Rsh degra	$RE_{R_{sh}}$	-0.1 $\pm$ 0.4	Overestimated	-4.6 $\pm$ 9.0	Overestimated	-4.1 $\pm$ 9.1	Overestimated

3.3. Correction performance using curves for defects of variable severity

In this subsection, the impact of each fault severity on correction performance is investigated. The severities of PS, Rs, and Rsh degradations are varied in the following ranges one at a time: GainPS = 0:0.1:1, $R_{s_degra} = 10^{-5}:0.2:2 \Omega$ or R_{sh_degra}

282 $=10^{1:1.5} \Omega$. For each fault level, the curves are simulated for the selected 174 pairs of G and Tm (presented in Section 3.1),
 283 and corrected using the three single-curve based methods.

284 3.3.1. CE and RE of key curve parameters

285 The performance metrics extracted from these corrected curves are now presented in Fig. 5 as a function of fault severity.

286
 287 Fig. 5 CE and RE of P_m , V_{oc} and I_{sc} using M1, M2 and NewM2 under 3 faulty conditions with variable fault severity: (a) PS, (b) Rs
 288 degradation, (c) Rsh degradation (the marked line represents the mean of 174 values obtained from the correction of 174 under each
 289 fault severity, while the band area behind represents the standard deviation; the x -axis for Rsh degradation is set as log scale; the
 290 degree of severity is presented from healthy to severe on the x -axis from left to right)

291 From Fig. 5, several remarks can be drawn:

- 292 • All the metrics have a monotonic variation with the fault severities;
- 293 • CE is mainly sensitive to PS and severe Rsh degradation;
- 294 • RE_{P_m} is more sensitive to severe Rsh degradation and PS. The step variation observed for PS is due to the
 295 maximum power point (MPP) shifting as it can be observed in Fig. 6;
- 296 • $RE_{V_{oc}}$ and $RE_{I_{sc}}$ are almost insensitive to all faults regardless of their level of severity, except for $RE_{I_{sc}}$ under
 297 severe Rs degradation;
- 298 • The overall performance of NewM2 is better than M1 and M2 with relatively lower CE and RE for key curve
 299 parameters.

Fig. 6 Corrected curves and RE_{P_m} using M1, M2 and NewM2 under three fault severities of PS: (a) GainPS = 0.6, (b) GainPS = 0.4, (c) GainPS = 0.2 (the displayed color of corrected curves and MPP depends on the G of the curve to correct, the circles on the curves represent the MPP, RE_{P_m} are marked as 'mean'±'std')

Moreover, it should be noted that, for P_m , which serves as an essential indicator for PV devices' health status, its RE is always positive and gradually increases with the fault severity. This means that using M1 or M2 leads to an inevitable underestimation of the fault impact, which increases with the fault severity.

3.3.2. RE of fault features

The impact of fault severity on fault features is also investigated, as illustrated in Fig. 7.

Fig. 7 RE of fault features under PS, R_s and R_{sh} degradations with variable fault severity (the marked line represents the mean of 174 values obtained from the correction of 174 curves under each fault severity, while the band area behind represents the standard deviation; the x -axis for R_{sh} degradation is set as log scale; the degree of severity is presented from healthy (except for V_{rp} and I_{rp} as these features do not exist under healthy condition) to severe on the x -axis from left to right)

Concerning the variation of the defect characteristics, different trends are observed: for the features V_{rp} and R_s using all the three methods and for R_{sh} using M1, the RE decreases as the severity of the defect increases. The opposite trend is observed for the other cases. This is due to the different changing rates of each feature's absolute error and its reference value, as defined in (12). Overall, NewM2 performs relatively better with lower and more stable RE .

It should be noted that within the range of severity of the defects tested; all characteristics are underestimated with the three methods. Therefore, used as defect signatures (R_s or R_{sh} , for example), which is typical for PV module degradation analyses, this could hamper the detection and diagnosis of these defects.

4. Performance of correction methods using multiple I-V curves

In this section, the method based on multiple curves (M3) will be evaluated. Section 4.1 presents the selection of G and T_m for the reference curves. Sections 4.2 and 4.3 present the correction performance using simulated curves with the selected G and T_m , for constant and then variable fault severity.

4.1. Selection of G and T_m for reference curves

Different from M1 and M2, M3 needs at least three reference curves to complete one correction to STC. In this study, like other common applications of M3, we apply the 2-step correction methodology proposed in (IEC 60891, 2009) with three curves. An illustration of this methodology on G - T_m plot is shown in Fig. 8.

330

331 Fig. 8 Illustration of 2-step correction methodology based on three curves (Step 1: use reference curves 1 and 2 to generate the interim
332 curve; Step 2: use reference curve 3 and the interim curve to get the final corrected curve)

333 Before the simulation of these curves, G and T_m need to be determined. The field-measured distributions of G and T_m of
334 the same mc-Si module employed in the simulation represent as many real situations as possible. As shown in Fig. 8, three
335 reference curves form one group of curves to get one corrected-to-STC curve. The irradiance G and temperature T_m of
336 these reference curves are determined by one-day measurement, covering sunny and cloudy conditions. The latter have
337 larger fluctuations of T_m . Besides, for sunny and cloudy conditions, three possible conditions are also considered for the
338 irradiance: 1) lower than 1000 W/m², 2) around 1000 W/m² and 3) higher than 1000 W/m². In total, 120 groups of G and
339 T_m are manually selected. Some examples are shown in Fig. 9.

340

341 Fig. 9 Examples of selected G and T_m from different summer days: (a, b, c) clear sunny days, (d, e, f) cloudy days ((a, d): the 3
342 selected $G < 1000$ W/m², (b, e): selected G around 1000 W/m², (c, f): selected $G > 1000$ W/m²)

343

4.2. Correction performance using field-measured G and T_m for defect of constant fault severity

345 Firstly, we use the same fault configuration presented in Section 3.1 and simulate 120 groups of reference curves regarding
346 the fault severity setting. Then, M3 is applied to obtain 120 corrected curves, as shown in Fig. 10. The corresponding
347 performance metrics and fault features are summarized in Table 5.

348

Fig. 10 Corrected curves using M3 (for PS, due to the large fluctuations, the corrected curves are plotted with dot line for better presentation)

Table 4 Four metrics to present the correction performance and the impact of correction on fault features using M3

Case	CE (%) (mean ± std)	RE_{P_m} (%) (mean ± std)	$RE_{V_{OC}}$ (%) (mean ± std)	$RE_{I_{SC}}$ (%) (mean ± std)	Fault feature		
					Feature	Value (%) (mean ± std)	Impact on fault feature
Healthy	0.18±0.10	-0.02±0.1	0.07±0.04	$6.10^{-3} \pm 0.05$	-	-	-
PS	3.67±2.38	7.5±18.3	0.06±0.07	$6.10^{-3} \pm 0.05$	$RE_{V_{rp}}$	-6.9±32.0	Overestimated
					$RE_{I_{rp}}$	3.2±12.2	Underestimated
SC	0.28±0.16	0.03±0.3	0.2±0.1	$6.10^{-3} \pm 0.05$	$RE_{V_{OC}}$	0.2±0.1	Underestimated
OC	0.18±0.06	2e-4±0.2	0.07±0.05	$6.10^{-3} \pm 0.05$	$RE_{I_{SC}}$	$6.10^{-3} \pm 0.05$	Underestimated
Rs degra	0.13±0.07	0.1±0.2	0.07±0.03	$6.10^{-3} \pm 0.05$	RE_{R_s}	0.01±0.04	Overestimated
Rsh degra	0.36±0.14	0.4±0.2	0.05±0.04	$6.10^{-3} \pm 0.05$	$RE_{R_{sh}}$	$4.10^{-3} \pm 0.01$	Underestimated

From the results, clearly, except for PS, M3 achieves good correction (mean value of all metrics within $\pm 1\%$) for all the conditions.

In the following, we analyze the ‘catastrophic’ correction error near the inflexion point under PS. As illustrated in Fig. 8, the correction procedure using M3 is done in two steps. An example of these steps under PS is shown in Fig. 11. In step 1, due to the unsynchronized appearance of inflexion points on reference curves 1 and 2 (i.e., V_{rp} are not identical), another inflexion point is created on the intermediate curve, so that in step 2, a strange curve shape is introduced. This phenomenon could lead to a large error on P_m but with no significant impact on V_{OC} and I_{SC} .

Fig. 11 Correction procedure under PS using 3 reference curves-based M3: (a) correction step 1, (b) correction step 2

Also, it should be noted that the fault impact on all the fault features is underestimated. Furthermore, as expected, the most significant error occurs under PS. Under the other conditions, the RE is within $\pm 1\%$.

4.3. Correction performance using field-measured G and T_m for defects of variable severity

In this subsection, the impact of fault severity on correction performance using M3 is investigated. The severity for PS, Rs and Rsh degradations is varied using the same setting as in Section 3.2. The performance metrics as a function of fault severity are presented in Fig. 12.

Fig. 12 CE and RE of P_m , V_{oc} and I_{sc} for M3 under 3 faulty cases with variable fault severity: (a) PS, (b) R_s degradation, (c) R_{sh} degradation (the circled line represents the mean value for the 120 corrected curves for each fault severity, while the band area behind represents the standard deviation; the x -axis for R_{sh} degradation is set as log scale; the degree of severity is presented from healthy to severe on the x -axis from left to right)

From these results, the following remarks could be drawn:

- Regarding R_s and R_{sh} degradations, all the metrics are insensitive to the fault level;
- Regarding PS, only CE and RE_{P_m} vary according to the fault severity. CE has a monotonic variation, which makes it relevant for fault severity estimation. However, RE_{P_m} is not a reliable feature as it exhibits a non-monotonic variation. This phenomenon is due to the displacement of the maximum power point (MPP) as illustrated in Fig. 13.

Fig. 13 Corrected curves using M3 under 3 fault severities of PS: (a) $\text{GainPS}=0.8$, where MPP of real and corrected curves are all at 'lower stair', (b) $\text{GainPS} = 0.3$, where MPP of real is at 'upper stair' while MPP of most corrected curves at 'lower stair' (c) $\text{GainPS} = 0$, MPP of real and most corrected curves are all at 'upper stair' (for each case, RE_{P_m} is marked as 'mean' $\pm$ 'std')

The behavior of fault features is also investigated with the comparison of identified features from both corrected and real I-V curves presented in Fig. 14 and the corresponding relative errors (RE) in Fig. 15.

Fig. 14 Identified feature from corrected (using M3) and original I-V curve for fault of variable severity (the circled line represents the mean, while the band area represents the standard deviation; the values of R_s or R_{sh} identified from I-V curve are not equal to the additional resistance (illustrated in Fig. 1) due to the existence of inherent equivalent R_s (0.74Ω) or R_{sh} (708.36Ω) of PV arrays

Fig. 15 RE of fault features under PS, R_s and R_{sh} degradations for fault of variable severity using M3 (the circled line represents the mean, while the band area represents the standard deviation)

The large dispersion observed for $RE_{V_{rp}}$ and $RE_{I_{rp}}$ confirms the poor performance of the correction near the inflection point. The values of R_s and R_{sh} extracted from the original and corrected curves are very close, as confirmed in Fig. 14. This is also reflected in the low values of RE_{R_s} and $RE_{R_{sh}}$ displayed in Fig. 15. The mean value of RE_{R_s} lies within $\pm 0.1\%$ and that of $RE_{R_{sh}}$ within $\pm 0.2\%$, and both are relatively insensible to the varying fault severity. It is also noted that the standard deviations of RE_{R_s} and $RE_{R_{sh}}$ exhibit a decreasing trend when the fault severity increases. In all, with varying fault, M3 achieves quite good and robust correction under R_s and R_{sh} degradation.

5. Discussion

5.1. Summary of correction methods

The correction performance using three single and one multiple curves-based methods has been evaluated. Each method has its own pros and cons listed in Table 6.

Table 6 Pros and Cons of correction methods

	Single curve-based methods			Multiple curves-based method (M3)
	M1	M2	NewM2	
Pros	<ul style="list-style-type: none"> Better correction of voltage than M2 Suitable for rapid field diagnosis 	<ul style="list-style-type: none"> Better correction of current than M1 	<ul style="list-style-type: none"> Better overall performance than M1 and M2 	<ul style="list-style-type: none"> High-precision correction performance under most conditions Free of correction coefficients
Cons	<ul style="list-style-type: none"> Needs to determine the correction coefficients Prone to large underestimation of P_m, and fault features 			<ul style="list-style-type: none"> Not suitable for rapid field diagnosis Needs at least 3 well-chosen reference curves Poor correction near inflexion point under PS with high effect on P_m

Once established (i.e., correction coefficients determined), all these single curve-based correction methods can conduct rapid correction of measured I-V curves. This allows their integration in real-time health monitoring of PV devices. However, as discussed in Section 2.2, the determination of correction coefficients is a troublesome task. The coefficients determined using simulated data do not always fit the real values, especially for the installed PV panels after a long-time operation. The proposed NewM2, which combines M1 and M2's advantages, leads to better correction performance in all

fault conditions tested. However, it still introduces a significant correction error in the case of partial shading (PS), the degradation of R_s and R_{sh} , compared to healthy conditions, short circuit (SC) and open circuit (OC).

As for the multiple-curves-based method (M3), except under PS, excellent correction is obtained. However, the selection of reference curves is still a manual process (Hishikawa et al., 2016; IEC 60891, 2009), which could hinder its application in rapid or on-line field correction.

5.2. Suggestions for future work

Based on comparing the three IEC 60891 correction methods and the new proposal, some suggestions on future work are hereafter presented.

For correction methods based on a single curve, the determination of correction coefficients for PV panels on-site remains difficult. A strategy for determining these coefficients based on field measured data needs to be developed that differs from the IEC 60891 procedure, which requires environmental conditions that are only practically feasible in fully equipped laboratories. Solutions to reduce dependence on correction coefficients, such as (Hishikawa et al., 2019, 2018), should also be further developed and validated with I-V curves taken from panels with defects.

The proposed new correction method still needs to be evaluated with more types of defects.

For the correction method based on multiple curves, two improvements are expected. On the one hand, efforts are needed to improve correction performance in case of partial shading; on the other hand, developing a methodology for automatic and efficient selection of reference curves would facilitate the deployment of the technique in the field.

Correction methods should be evaluated with field-measured data.

6. Conclusion

In this work, we have evaluated the performance of methods based on one or more curves proposed in the IEC 60891 standard for the correction of I-V curves measured on defective photovoltaic panels. It has been shown that all the methods introduce significant errors due to irradiance, module temperature and the severity of the defects. Using the standard method M1 of the IEC, we have pointed out that a distortion of the curve's shape is commonly introduced with a relative error up to 13.8%. For P_m and the fault characteristics extracted from the corrected curves, estimation errors also occur frequently. Even worse still, most significant errors result in underestimating the characteristics (up to 9.1% for P_m using M2). This can affect the detection of incipient PV defects if these characteristics are used as defect signatures.

Among the single curve-based methods (M1 and M2), none of them could outperform under all the faulty simulated conditions. Therefore, an M2-based improved method (NewM2) has been proposed. It has exhibited more robust overall performance than M1 and M2 with the decrease of average curve error from 3.45% to 2.37%.

The method based on multiple curves (M3) generally has higher performance than those based on a single curve, but it is not suitable for rapid field diagnosis.

PV health monitoring and fault diagnosis using I-V curves is a promising approach. However, several signs of progress are expected from future work to improve its efficiency and ease its implementation. At first, the determination of correction coefficients based on field-measured data or mitigating the dependence on correction coefficients would be beneficial. Second, the development of a methodology for automatic determination of reference curves and improved correction performance (mainly to avoid underestimating incipient faults) under different faulty conditions.

Acknowledgment

The authors would like to acknowledge the SIRTAs for the field-measured data and the China Scholarship Council (CSC) for the PhD funding.

References

- Agrawal, N., Bora, B., Kapoor, A., 2020. Experimental investigations of fault tolerance due to shading in photovoltaic modules with different interconnected solar cell networks. *Sol. Energy* 211, 1239–1254. <https://doi.org/10.1016/j.solener.2020.10.060>
- Bouaichi, A., Alami, A., Hajjaj, C., Messaoudi, C., Ghennioui, A., Benlarabi, A., Ikken, B., El, A., Zitouni, H., 2019. In-situ evaluation of the early PV module degradation of various technologies under harsh climatic conditions : The case of Morocco. *Renew. Energy* 143, 1500–1518. <https://doi.org/10.1016/j.renene.2019.05.091>

465 Bühler, A.J., Perin Gasparin, F., Krenzinger, A., 2014. Post-processing data of measured I–V curves of photovoltaic
466 devices. *Renew. Energy* 68, 602–610. <https://doi.org/10.1016/j.renene.2014.02.048>

467 Chen, Z., Wu, L., Cheng, S., Lin, P., Wu, Y., Lin, W., 2017. Intelligent fault diagnosis of photovoltaic arrays based on
468 optimized kernel extreme learning machine and I-V characteristics. *Appl. Energy* 204, 912–931.
469 <https://doi.org/10.1016/j.apenergy.2017.05.034>

470 Chin, V.J., Salam, Z., Ishaque, K., 2015. Cell modelling and model parameters estimation techniques for photovoltaic
471 simulator application: A review. *Appl. Energy* 154, 500–519. <https://doi.org/10.1016/j.apenergy.2015.05.035>

472 Ding, K., Zhang, J., Bian, X., Xu, J., 2014. A simplified model for photovoltaic modules based on improved translation
473 equations. *Sol. Energy* 101, 40–52. <https://doi.org/10.1016/j.solener.2013.12.016>

474 Dolara, A., Lazaroiu, G.C., Leva, S., Manzolini, G., 2013. Experimental investigation of partial shading scenarios on PV
475 (photovoltaic) modules. *Energy* 55, 466–475. <https://doi.org/10.1016/j.energy.2013.04.009>

476 Fadhel, S., Delpha, C., Diallo, D., Bahri, I., Migan, A., Trabelsi, M., Mimouni, M.F., 2019. PV shading fault detection
477 and classification based on I-V curve using principal component analysis: Application to isolated PV system. *Sol.*
478 *Energy* 179, 1–10. <https://doi.org/10.1016/j.solener.2018.12.048>

479 Friesen, G., Herrmann, W., Belluardo, G., Herteleer, B., 2018. Report IEA-PVPS T13-11:2018 Photovoltaic module
480 energy yield measurements: Existing approaches and best practice, IEA-PVPS. URL [https://iea-pvps.org/wp-](https://iea-pvps.org/wp-content/uploads/2020/01/Photovoltaic_Module_Energy_Yield_Measurements_Existing_Approaches_and_Best_Practice_by_Task_13.pdf)
481 [content/uploads/2020/01/Photovoltaic_Module_Energy_Yield_Measurements_Existing_Approaches_and_Best_Pr-](https://iea-pvps.org/wp-content/uploads/2020/01/Photovoltaic_Module_Energy_Yield_Measurements_Existing_Approaches_and_Best_Practice_by_Task_13.pdf)
482 [actice_by_Task_13.pdf](https://iea-pvps.org/wp-content/uploads/2020/01/Photovoltaic_Module_Energy_Yield_Measurements_Existing_Approaches_and_Best_Practice_by_Task_13.pdf) (accessed 6.15.20).

483 Golive, Y.R., Singh, H.K., Kottantharayil, A., Vasi, J., Shiradkar, N., 2019. Investigation of Accuracy of various STC
484 Correction Procedures for I-V Characteristics of PV Modules Measured at Different Temperature and Irradiances,
485 in: 2019 IEEE 46th Photovoltaic Specialists Conference (PVSC). IEEE, Chicago, IL, USA, pp. 2743–2748.
486 <https://doi.org/10.1109/PVSC40753.2019.8980557>

487 Hishikawa, Y., Doi, T., Higa, M., Yamagoe, K., Ohshima, H., Takenouchi, T., Yoshita, M., 2018. Voltage-dependent
488 temperature coefficient of the I-V curves of crystalline silicon photovoltaic modules. *IEEE J. Photovoltaics* 8, 48–
489 53. <https://doi.org/10.1109/JPHOTOV.2017.2766529>

490 Hishikawa, Y., Ohshima, H., Higa, M., Yamagoe, K., Doi, T., 2016. Precise Determination of the STC I-V Curves by
491 Wide-Range Linear Extrapolation of Outdoor I-V Curves on Partly Sunny Days, in: 32nd European Photovoltaic
492 Solar Energy Conference and Exhibition (Eu-PVSEC). München, Germany, pp. 1716–1719.
493 <https://doi.org/10.4229/EUPVSEC20162016-5DO.11.4>

494 Hishikawa, Y., Takenouchi, T., Higa, M., Yamagoe, K., Ohshima, H., Yoshita, M., 2019. Translation of Solar Cell
495 Performance for Irradiance and Temperature from a Single I-V Curve Without Advance Information of Translation
496 Parameters. *IEEE J. Photovoltaics* 9, 1195–1201. <https://doi.org/10.1109/JPHOTOV.2019.2924388>

497 Huang, J.M., Wai, R.J., Gao, W., 2019. Newly-designed fault diagnostic method for solar photovoltaic generation system
498 based on IV-Curve measurement. *IEEE Access* 7, 70919–70932. <https://doi.org/10.1109/ACCESS.2019.2919337>

499 Huawei, 2020. Smart I-V Curve Diagnosis. URL [https://solar.huawei.com/en-](https://solar.huawei.com/en-GB/download?p=%2F-%2Fmedia%2FSolar%2Fattachment%2Fpdf%2F%2Fdatasheet%2FIV-Curve.pdf)
500 [GB/download?p=%2F-%2Fmedia%2FSolar%2Fattachment%2Fpdf%2F%2Fdatasheet%2FIV-Curve.pdf](https://solar.huawei.com/en-GB/download?p=%2F-%2Fmedia%2FSolar%2Fattachment%2Fpdf%2F%2Fdatasheet%2FIV-Curve.pdf)
501 (accessed 8.17.20).

502 IEC 60891, 2009. Photovoltaic devices - Procedures for temperature and irradiance corrections to measured I-V
503 characteristics.

504 Li, Y., Ding, K., Zhang, J., Chen, F., Chen, X., Wu, J., 2019. A fault diagnosis method for photovoltaic arrays based on
505 fault parameters identification. *Renew. Energy* 143, 52–63. <https://doi.org/10.1016/j.renene.2019.04.147>

506 Ma, M., Liu, H., Zhang, Z., Yun, P., Liu, F., 2019. Rapid diagnosis of hot spot failure of crystalline silicon PV module
507 based on I-V curve. *Microelectron. Reliab.* 100–101. <https://doi.org/10.1016/j.microrel.2019.113402>

508 Martínez-Moreno, F., Figueiredo, G., Lorenzo, E., 2018. In-the-field PID related experiences. *Sol. Energy Mater. Sol.*

Cells 174, 485–493. <https://doi.org/10.1016/j.solmat.2017.09.037>

Mellit, A., Tina, G.M., Kalogirou, S.A., 2018. Fault detection and diagnosis methods for photovoltaic systems: A review. *Renew. Sustain. Energy Rev.* 91, 1–17. <https://doi.org/10.1016/j.rser.2018.03.062>

Migan, A., Mambrini, T., Bourdin, V., Badosa, J., 2015. Deployment of a multi-technology photovoltaic module test bench on the SIRTa meteorological and climate observatory, in: 31st European PV Solar Energy Conference and Exhibition (Eu-PVSEC). Hamburg, Germany.

Pillai, D.S., Rajasekar, N., 2018. A comprehensive review on protection challenges and fault diagnosis in PV systems. *Renew. Sustain. Energy Rev.* 91, 18–40. <https://doi.org/10.1016/j.rser.2018.03.082>

Rajput, P., Tiwari, G.N., Sastry, O.S., Bora, B., Sharma, V., 2016. Degradation of mono-crystalline photovoltaic modules after 22 years of outdoor exposure in the composite climate of India. *Sol. Energy* 135, 786–795. <https://doi.org/10.1016/j.solener.2016.06.047>

Sarikh, S., Raoufi, M., Bennouna, A., Benlarabi, A., Ikken, B., 2020. Implementation of a plug and play I-V curve tracer dedicated to characterization and diagnosis of PV modules under real operating conditions. *Energy Convers. Manag.* 209. <https://doi.org/10.1016/j.enconman.2020.112613>

Silva, A.M., Melo, F.C., Reis, J.H., Freitas, L.C.G., 2019. The study and application of evaluation methods for photovoltaic modules under real operational conditions, in a region of the Brazilian Southeast. *Renew. Energy* 138, 1189–1204. <https://doi.org/10.1016/j.renene.2019.01.129>

Spataru, S., Sera, D., Kerekes, T., Teodorescu, R., 2015. Monitoring and Fault Detection in Photovoltaic Systems Based On Inverter Measured String I-V Curves, in: 31st European Photovoltaic Solar Energy Conference and Exhibition (EU PVSEC). Hamburg, Germany, pp. 1667–1674. <https://doi.org/10.4229/EUPVSEC20152015-5BO.12.2>

Tanesab, J., Parlevliet, D., Whale, J., Urmee, T., 2017. Seasonal effect of dust on the degradation of PV modules performance deployed in different climate areas. *Renew. Energy* 111, 105–115. <https://doi.org/10.1016/j.renene.2017.03.091>

Tanesab, J., Parlevliet, D., Whale, J., Urmee, T., Pryor, T., 2015. The contribution of dust to performance degradation of PV modules in a temperate climate zone. *Sol. Energy* 120, 147–157. <https://doi.org/10.1016/j.solener.2015.06.052>

Triki-Lahiani, A., Bennani-Ben Abdelghani, A., Slama-Belkhodja, I., 2018. Fault detection and monitoring systems for photovoltaic installations: A review. *Renew. Sustain. Energy Rev.* 82, 2680–2692. <https://doi.org/10.1016/j.rser.2017.09.101>

Wang, M., Liu, J., Burleyson, T.J., Schneller, E.J., Davis, K.O., French, R.H., Braid, J.L., 2020. Analytic I_{sc} – V_{oc} Method and Power Loss Modes From Outdoor Time-Series I_{sc} – V_{sc} Curves. *IEEE J. Photovoltaics* 10, 1379–1388. <https://doi.org/10.1109/JPHOTOV.2020.2993100>

Zhu, H., Lu, L., Yao, J., Dai, S., Hu, Y., 2018. Fault diagnosis approach for photovoltaic arrays based on unsupervised sample clustering and probabilistic neural network model. *Sol. Energy* 176, 395–405. <https://doi.org/10.1016/j.solener.2018.10.054>

Zhu, Y., Xiao, W., 2020. A comprehensive review of topologies for photovoltaic I–V curve tracer. *Sol. Energy*. <https://doi.org/10.1016/j.solener.2019.12.020>